

Gas Resistant DPC CE Mark to EN 14909



- Complies with BS8485:2015 for gas protection
- Tested & passed to ISO 15105-1 methane permeability method
- Aluminium foil to resist methane, radon, CO2 and low levels of hydrocarbon
- Easy to apply using traditional methods
- Independently assessed

DESCRIPTION

Visqueen Gas Resistant (GR) Damp Proof Course is a flexible polyethylene DPC with an aluminium foil designed to prevent the transmission of carbon dioxide, radon, methane and low level hydrocarbon vapours. This is in addition to the product's usage as a damp proof course. Resistance to harmful gases is achieved by an integral aluminium film.

APPLICATION

Visqueen Gas Resistant (GR) DPC should be used on any site where carbon dioxide, radon, methane or low level hydrocarbon vapours are a problem. Methane can occur in any construction on any site previously used for landfill. Such conditions can exist on household, commercial and industrial sites. Visqueen Gas Resistant (GR) DPC has excellent physical characteristics and good cold flexibility performance. It is suitable for vertical, horizontal, stepped and cavity tray applications.

Good Practice Tip

To avoid slip or shear planes it is not recommended to take membranes through the wall. In order to provide a continuous barrier across the cavity Visqueen Gas Resistant DPC should be sealed to the membrane, taken through the blockwork, up the wall and incorporated below the damp proof course on the cavity tray outer leaf

IMPORTANT

Where the DPC may be in direct contact with hydrocarbon contamination the use of Visqueen GX DPC must be considered.

The DPC must be installed with the black side facing up.

System components and jointing

All DPC laps must be a minimum of 100mm and bonded together with Visqueen Zedex DPC Jointing Tape.

Installation

Visqueen Gas Resistant (GR) DPC should be installed in accordance with BS 8215:1991, BS 8000: Part 3, 2001 and BS 5628: Part 3, 2005. All horizontal DPCs must be bedded on both sides with fresh mortar. All DPCs must project through the full width of the wall, including any externally applied rendering and project 5mm beyond the finished external face. All cavities must be kept clear of mortar droppings and other debris. Any mortar droppings reaching the DPCs must be removed before they harden, avoiding the use of sharp objects for removal. Reference should also be made to NHB C guidance notes and BRE Report BR211.

The DPC must be installed with the black side facing up.

All DPC laps must be a minimum of 100mm and bonded together with Visqueen Zedex DPC Jointing Tape.

STORAGE AND HANDLING

Visqueen Gas Resistant (GR) DPC is classified as non-hazardous when used in accordance with the relevant British Standards. The product is chemically inert and is not

Gas Resistant DPC CE Mark to EN 14909

Page 2

The DPC should be stored in a warm, dry and environment above 5oC.

Technical Data and CE Mark

Visqueen Gas Resistant Damp Proof Course complies with the requirements and clauses of EN 14909 - Flexible sheets for waterproofing - Plastic and rubber damp proof courses - Definitions and characteristics.

Visqueen Gas Resistant DPC products are manufactured under a Quality Management System (ISO 9001) - Certificate of Compliance reference no. 4560-3 by Knight International applies.



Product Data

Product Data

Characteristic	Test method	Units	Compliance criteria	Value or Statement
Visible defect	EN 1850 -2	-	Pass/Fail	Pass
Length	EN 1848-2	m	-0%/+10%	30
Width	EN 1848-2	m	-0%/+10%	0.5 to 1
Straightness	EN 1848-2	-	Pass/Fail	Pass
Thickness	EN 1849-2	mm	-20%/+20%	0.5
Mass	EN 1849-2		-12%/+12%	257;379;475
Watertightness	EN 1928	-	Pass/Fail	Pass
Resistance to impact	EN 12691	mm	>MLV	40
Durability (artificial ageing)	EN 1296 and EN 1928	-	Pass/Fail	Pass
Durability (alkali)	Annex C	-	Pass/Fail	NPD
Resistance to low temperature	EN 495-5	?C	<MLV	-40
Resistance to tearing (nail shank)	EN 12310-1	N	MDV	280 310
Water vapour permeability properties	EN 1931		+/-20%	0.13
Resistance to static loading	EN 12730	Kg	>MLV	20
Reaction to fire	EN 13501-1		Class	F
Methane Permeability	ISO 15105-1		MDV	13
Reaction to Fire	EN 13501-1	Class	MDV	F



Gas Resistant DPC CE Mark to EN 14909

Appendix A

About Visqueen

Visqueen is the market leader in the manufacture and supply of structural waterproofing and gas protection systems. Visqueen offers the complete package – a proven, reliable range backed by a technical support service that goes unmatched in the market - everything you would expect from a reputable and ethical company.

Complete Range, Complete Solution

- Structural Waterproofing
- Damp Proof Course
- Damp Proof Membranes
- Gas Protection and Gas Venting
- Vapour Control Layers
- Stormwater Protection

Download Library

- Technical Datasheet
- Standard Details
- Technical Service
- Visqueen Gas Protection Brochure
- NBS Clauses
- BBA Certificates
- Material Safety Datasheets
- Specification Guide

Find your local stockist

Search our directory of Visqueen specification [Specialist Centres](#) to locate your nearest Visqueen Partner.

Technical support throughout your project

We are specialists in our field and can help you specify the correct solutions with the necessary performance levels, in accordance with building regulations.

- Nationwide site support team
- Specification advice
- Installation guidance & project sign off
- System design including CAD details

CPD Seminars and Training Academy



Gas Protection CPD

The specification, technical design, and installation of gas protection systems, enabling the sustainable regeneration of brownfield sites.



Structural Waterproofing CPD

The specification, technical design, and installation of structural waterproofing systems for protection against water and damp ingress in both above and below ground projects.



Visqueen Training Academy

We are now able to offer exclusive in depth training opportunities on a wide variety of Visqueen products at our Training Academy.



Visqueen Special Projects

We provide high-level expertise, comprehensive support and experience in all types of waterproofing and gas protection.

VISQUEEN

Part of RPC bpi group

Heanor Gate Road, Heanor, Derbyshire, DE75 7RG

0333 202 6800 enquiries@visqueen.com www.visqueen.com

The information given in this datasheet is based on data and knowledge correct at the time of printing. Statements made are of a general nature and are not intended to apply to any use or application outside any referred to in the datasheet. As conditions of usage and installation are beyond our control we do not warrant performance obtained but strongly recommend that our installation guidelines and the relevant British Standard Codes of Practice are adhered to. Please contact us if you are in any doubt as to the suitability of application.

