

Technical support: +44 (0) 333 202 6800

Date Published: 20/05/2024

Visqueen Gas Resistant Self Adhesive Membrane

- BBA certified third party accreditation
- Type A Barrier Membrane (Tanking Membrane) resistant to ground water in accordance with BS 8102:2022
- Complies with the methane gas transmission rate, mass per unit area and thickness requirements of BS 8485:2015 + A1:2019 industry standard for methane and carbon dioxide protection
- Also provides radon and damp proof membrane protection
- Self adhesive application no jointing tapes required

Visqueen Gas Resistant Self Adhesive Membrane is a foil lined modified bitumen rubber membrane with a self adhesive coating protected by a removable polyethylene release film. The product is silver on the upper surface and supplied in rolls 1m x 20m.

Approvals and standards

- Third party accreditation (BBA 15/5208)
- Suitable for use as a Type A Barrier Membrane (Tanking Membrane) to BS 8102:2022
- Conforms to the specification requirements of BS 8485:2015 + A1:2019
- Conforms to the specification requirements of BR 211: 2023
- UKCA UKNI CE to EN 13969:2004
- Visqueen certified with Quality Management System ISO 9001:2015
- Visqueen certified with Occupational Health and Safety System ISO 45001:2018
- Visqueen certified with Environmental Management System ISO 14001:2015

Usage

Visqueen Gas Resistant Self Adhesive Membrane is a cold applied product, suitable for use as a Type A Barrier Membrane (Tanking Membrane) for above and below ground applications e.g. basements, retaining walls and lift pits.

It is also suitable for use in all types of buildings to prevent the ingress of harmful levels of ground gases e.g. methane, carbon dioxide and radon.

The membrane can be applied to a variety of substrates including concrete, flush pointed blockwork, flush pointed brickwork, particle boards and steelwork, in both vertical and horizontal applications.

The membrane can be used to achieve one form of waterproofing to Grades 1, 2 and 3 as defined in BS 8102:2022.

System components

- Visqueen HP Tanking Primer, 5L
- Visqueen Ultimate Top Hat Units
- Visqueen TreadGUARD 1500, 1m x 2m
- Visqueen Protect&Drain
- Visqueen Pile Cap Sealer, 25kg
- Visqueen IGW5 and IGW10 Waterstops



Technical support: +44 (0) 333 202 6800

Date Published: 20/05/2024

Visqueen Gas Resistant Self Adhesive Membrane

Storage and handling

Visqueen Gas Resistant Self Adhesive Membrane should be stored vertically under cover in its original packaging.

Care should be taken when handling the product in line with current manual handling regulations.

Preparation

All surfaces to which Visqueen Gas Resistant Self Adhesive Membrane are to be applied should be free from cavities or projections, have a smooth finish, be dry and free from dust, loose particles and frost. Masonry, concrete or metal surfaces should be primed using Visqueen HP Tanking Primer and allowed to dry thoroughly.

When applying to blockwork or brickwork the joints must be flush pointed or the masonry rendered prior to applying the

The membrane can be cut with a sharp retractable safety knife.

Installation

Visqueen Gas Resistant Self Adhesive Membrane lap joints should be a minimum of 150mm and should be pressed and rollered to form a continuous bond and to ensure watertightness.

At 90 degree changes of direction a Visqueen Axiom UniSeal fllet should be formed prior to membrane installation.

For vertical applications cut the membrane to a suitable length allowing an additional 150mm for laps. Position and peal back release film and apply the self adhesive face to the substrate. Apply pressure to ensure a full bond is achieved. Commence at the top of the wall and work downwards, progressively removing the release film.

For horizontal applications unroll the membrane where required allowing an additional 150mm for laps. Re-roll one half of the membrane and cut release film taking care not to damage the membrane. Roll out the membrane progressively removing the release film. Press the membrane onto the substrate e.g. using a soft broom to ensure full adhesion. Repeat for the other half of the

Watertight seals should be formed around all service entry points. Visqueen Preformed Top Hat Units should be used for sealing service entry pipes.

If the membrane is punctured or perforated, a patch of the same material should be lapped and bonded at least 150mm beyond the extents of the puncture.

The membrane should always be fully protected immediately after it is installed. When used externally on a retaining wall, the membrane should be protected from backfill with Visqueen Protect&Drain, which also provides a preferential pathway for ground gases.

When forming day joints, the upper edge of the membrane should be adequately secured e.g. bonding onto the top of the retaining wall, or if terminated on a vertical face, the upper edge should be secured with Visqueen Fixing Strip and Visqueen Fixings Pins for Masonry.

Usable temperature range

It is recommended that Visqueen Gas Resistant Self Adhesive Membrane and all associated system components should not be installed below 5°C.

The membrane requires no additional bonding methods however during cold weather conditions the application of hot air to the self adhesive coating will aid adhesion.

Additional information

Where hazardous ground gases are not present use Visqueen Self Adhesive Membrane

Where concrete construction joints occur Visqueen IGW Waterstop system should be incorporated

When waterproof concrete is required, or for additional detailing information, contact Visqueen Technical Services +44 (0) 333 202

The information in this datasheet was correct at the time of publication. It is the user's responsibility to obtain the latest version of the datasheet as it is updated on a regular basis. The information contained in the latest datasheet supersedes all previously published editions.



Date Published: 20/05/2024

Visqueen Gas Resistant Self Adhesive Membrane

VISQUEEN	GR SAM
----------	---------------

Property	Test method	Units	Compliance	Result
			criteria	
Length	BS EN 1848-2	m	-0%/+5%	20
Width	BS EN 1848-2	m	-5%/+5%	1
Thickness	BS EN 1849-2	mm	-5%/+10%	1.2
Mass	BS EN 1849-2	g/m²	-10%/+10%	1100
Watertightness to 60kPa for 24 hours	BS EN 1928	-	MDV	Pass
Durability after artificial ageing	BS EN 1847	-	Pass/Fail	Pass
Durability against chemicals	BS EN 1847	-	Pass/Fail	Pass
Resistance to tearing (nail shank) MD	BS EN 12310-1	N	>	100
Resistance to tearing (nail shank) CD	BS EN 12310-1	N	>	100
Resistance to static loading	BS EN 12730	kg	MLV	20
Resistance to Impact method A and B	BS EN 12691	mm	>	A >500 B >1000
Reaction to fire	BS EN 13501-1		Class	Е
Joint Resistance	BS EN 12317-1	N	>	30
Tensile properties - MD	BS EN 12311-2	N/mm²	>	2
Tensile properties - CD	BS EN 12311-2	N/mm²	>	2
Tensile elongation - MD	BS EN 12311-1	%	>	130
Tensile elongation - CD	BS EN 12311-2	%	>	130
Reaction to fire	BS EN 13501-1	Class	MDV	F
Methane permeability	ISO 15105-1	ml/m²/d	MDV	<1
Radon transmission rate	SP RI.SE	m/s	MDV	4.7 x 10 ⁻ 9
Radon permeability	SP RI.SE	m²/s	MDV	0.56 x 10 ⁻¹²
Mean water vapour resistance factor	BS EN 1931	(µ)	MDV	3960000
Mean water vapour diffusion equivalent air layer thickness	BS EN 1931	(Sd) in m	MDV	4752
Mean water vapour resistance	BS EN 1931	MNs/g	MDV	23760
Mean water vapour permeability	BS EN 1931	g/m²/day	MDV	0.03

Health and safety information

Refer to the Visqueen Gas Resistant Self Adhesive Membrane safety datasheet (SDS).

Technical Datasheet - Test Data

Technical support: +44 (0) 333 202 6800

Date Published: 20/05/2024

Visqueen Gas Resistant Self Adhesive Membrane

About Visqueen

The Visqueen name has long been recognised as one of the leading manufacturers of high quality advanced membrane technologies and design based solutions by specifiers, distributors, builders merchants and contractors throughout the UK and Europe.

For further guidance on the Visqueen services shown below, please refer to the relevant section of the Visqueen website (www.visqueen.com) or contact Visqueen Technical Services on +44 (0) 333 202 6800 or enquiries@visqueen.com

Complete Range, Complete Solution

















Structural Waterproofing

Gas Protection

Damp Proof Membrane

Tapes

Damp Proof Course

Stormwater

Vapour Control

Visqueen Technical Support

Visqueen combine an extensive product portfolio with industry leading levels of service and support which includes guidance over the phone, bespoke CAD drawings to help with complex detailing, electronic NBS specifications and access to a dedicated team of highly knowledgeable and experienced field based Technical Support Managers.

Visqueen Technical Support is available to all our customers including architects, specifiers, distributors, builders merchants, contractors and end users. All of our technical team have been awarded the industry recognised qualification Certificated Surveyor in Structural Waterproofing (CSSW).

Visqueen CPD Seminars

The Visqueen Continuing Professional Development (CPD) Seminars provide up-to-date information on changes within Building Regulations/Building Standards and nationally recognised industry guidance affecting damp proofing, water vapour control, hazardous ground gas protection and below ground structural waterproofing.

The one hour seminars have been produced for design specialists within the construction sector and are delivered by our team of Technical Support Managers.

Visqueen Training Academy

Based at our manufacturing facility in Derbyshire, the Visqueen Training Academy is available to support Visqueen customers throughout the UK by providing a wide range of both theory and practical skills related training.

Courses include one day product awareness training for our distributors and builders merchants to help them in their day-to-day jobs, through to intensive two day courses giving detailed hands-on training in the practical skills required for safe and robust product installation.